

Industrial Plastic Optocouplers

SO8 Package

Mechanical and Environmental Testing

Description

The reliability data in this document includes Broadcom reliability test data from the reliability tests done on this product family. All of these products use similar processes and materials. The data in [Table 1](#) and [Table 2](#) reflects actual test data for the devices. Before stress, all devices are preconditioned at MSL 1 using a solder reflow process (260°C peak temperature) and 20 temperature cycles (–55°C to +125°C, 15-minute dwell, 1-minute transfer). This data is taken from testing on Broadcom® devices using internal Broadcom processes, material specifications, design standards, and statistical process controls.

NOTE: This data is not transferable to other manufacturer's similar part types.

Definition of Failure

Abnormal resistance (meaning an open or short failure) is the definition of failure in this data sheet. Specifically, failure occurs when the device fails contact resistance either high or low, or both, and when the device experiences abnormal leakages, or both.

Reliability Testing

Broadcom subjects the devices to a series of reliability tests, including environmental, mechanical, and electrical tests, to ensure that the product meets the intended reliability expectations. The tables provided in this data sheet show the results of reliability testing conducted by Broadcom over a period of time as shown in the test conditions.

Table 1: Mechanical Tests (Testing Done on a Constructional Basis)

Test Name	Reference Standard	Test Conditions	Units Tested	Units Failed
Temperature Cycling	JESD-A104	–55°C to +125°C Transfer = 1 minute Dwell = 15 minutes 1000 cycles	3209	0
Solderability (RoHS Condition)	JESD-B102	8 hours steam aging (93°C), followed by solder dip (260°C, 5 seconds)	120	0
Physical Dimensions	JESD-B100	Conformance to data sheet package drawings	290	0
Preconditioning	J-STD-20 JA113	As per reference standard (to conform to MSL 1)	6203	0

Table 2: Environmental Tests (Testing Done on a Constructional Basis)

Test Name	Reference Standard	Test Conditions	Units Tested	Units Failed
Temperature-Humidity-Bias	JESD-A101	T _A = 85°C, RH = 85% Biased Time = 1000 hours	1060	0
Highly Accelerated Stress Test (HAST)	JESD-A110	T _A = 130°C, RH = 85% Biased Time = 96 hours	298	0
Unbiased HAST	JESD-A118	T _A = 130°C, RH = 85% Unbiased Time = 96 hours	856	0
Autoclave	JESD-A102	T _A = 121°C, RH = 100% Unbiased Time = 96 hours	639	0
High Temperature Bake	JESD-A103	T _A = 150°C Unbiased Time = 1000 hours	892	0

Copyright © 2016–2023 Broadcom. All Rights Reserved. The term “Broadcom” refers to Broadcom Inc. and/or its subsidiaries. For more information, go to www.broadcom.com. All trademarks, trade names, service marks, and logos referenced herein belong to their respective companies.

Broadcom reserves the right to make changes without further notice to any products or data herein to improve reliability, function, or design. Information furnished by Broadcom is believed to be accurate and reliable. However, Broadcom does not assume any liability arising out of the application or use of this information, nor the application or use of any product or circuit described herein, neither does it convey any license under its patent rights nor the rights of others.